

Strontium Sulfide

Powder

Parameter	Result
SrS (Iodine Titration)	60.0 – 70.0 %
BaS	0.6 %
Moisture	0.3 %
Residue on > 200 mesh	max 3.0 %
Further specifications and special types on request.	

Granular

Parameter	Result
SrS (Iodine Titration)	60.0 – 70.0 %
BaS	max 0.6 %
Moisture	0.3 %
Residue on > 8 mesh	max 8.0 %
Further specifications and special types on request.	

ABASSCO. ASIA BARIUM & STRONTIUM SALTS CO.



KM 125 Tehran-Semnan Road, 35815-343, Iran.

Email : info@abassco.com

WWW.ABASSCO.COM

Tel : +98 23 3454 4470/2

Fax : +98 23 34542079

Disclaimer: The information contained in is for general information purposes only, while we endeavor to keep the information up to date and correct. We make no representations or warranties of any kind, express or implied, about the completeness, accuracy, reliability or availability with respect to this or the information. Any reliance you place on such information is therefore strictly at your own risk. The user should not assume that all measures are indicated or that other measures may not be required.